

CONVERUST^{EPOXY}

RC 900

Rev. 24/04/2002

Product Description

DINITROL CONVERTRUST EPOXY actively converts the rust on substrates to a stable organic iron complex. Free of lead zinc and chromium. The product is overpaintable after its hardened.

Application

Remove loose rust, grease and dirt by using a brush, sandpaper or a sandblast. Shake the spray can well. Apply the spray two or three times deeply, spray distance approx. 25 cm when applying, the metal temperature should not be below 10°C. If spraying equipment is used it is very important that it is cleaned with universal-dilution promptly and blown dry with compressed air.

Technical Data

Colour	amber
Density	0,837 kg/m ³
Shelf life	72 months
Solids content	0,8%

Available in

SIZE	PACKAGE	ART NO
400 ml	aerosol	11008



DINOL AB, Box 149, SE-281 22 Hässleholm, Sweden
Telephone +46 451 880 00. Telefax +46 451 880 88.

CONVERUST^{EPOXY}
RC 900