



Brunel Close, Park Farm
 Wellingborough
 Northants
 NN8 6QX
 01933 675299
 01933 670800
 ISS 2.0 18/02/02

STAINLESS STEEL PUTTY (ST)

PRODUCT DATA SHEET

Stainless Steel Putty is a steel filled epoxy putty for rust-free maintenance and repair work.

FEATURES

- Chemically accepted for use in USDA inspected plants.
- Cures at room temperature
- Non-rusting and stainless steel finish
- Bonds to ferrous and non-ferrous metals, wood and concrete
- Conventional metalworking tools can be used to drill, tap or grind cured repairs
- Excellent chemical resistance
- Has FDA approval

RECOMMENDED APPLICATIONS

- Patches, repairs and rebuilds stainless steel equipment in areas where welding is impractical or impossible
- Repairs cracks, dents and breaks in equipment, machinery or castings.
- Rebuilds shafts, trays and chutes.
- Used for repairs in dairies and food processing operations and chemical plants
- Certified for portable water applications

PRODUCT DATA :

Typical Properties

Colour.....	Grey
Pot life at 21°C.....	45 minutes
Mixed consistency.....	Putty
Adhesive tensile shear ASTM D 1002.....	21 N/mm ²
Compressive Strength ASTM D 695.....	61 N/mm ²
Operating temperature, maximum	121°C
Cured hardness, Shore D ASTM D 2240.....	85
Specific Volume	447 cm ³ / kg
Coverage, cm ³ /kg @ 5mm thickness	700
Dielectric strength volt/mil	30
Mix ratio.....Weight	11:1
Cure shrinkage cm/cm ASTM D 2566.....	0.001

CHEMICAL RESISTANCE 7 Days room temperature cure (30 days immersion @ 21°C)

Kerosene	Very Good	Methanol	Unsatisfactory
Hydrochloric acid 10%	Fair	Toluene	Very Good
chlorinated solvent	Very Good	Ammonia	Very Good
Sulphuric Acid 10%	Very Good	Sodium Hydroxide 10%	Unsatisfactory

Please consult ITW Devcon for other chemicals.



Brunel Close, Park Farm
Wellingborough
Northants
NN8 6QX
01933 675299
01933 670800
ISS 2.0 18/02/02

Epoxies are very good in water, saturated salt solution, leaded gasoline, mineral spirits, ASTM #3 oil and propylene glycol. Epoxies are generally not recommended for long term exposure to concentrated acids and organic solvents.

APPLICATION INFORMATION

General Surface Preparation:

Proper surface preparation is essential to a successful application. The following procedures should be considered:

- All surfaces must be dry, clean and rough.
- If surface is oily or greasy, use Devcon Fast Cleaner 2000 Spray / Cleaner Blend 300 to degrease the surface.
- Remove all paint, rust and grime from the surface by abrasive blasting or other mechanical techniques.
- Aluminium repairs: Oxidation of aluminium surfaces will reduce the adhesion of an epoxy to a surface. This film must be removed before repairing the surface, by mechanical means such as grit-blasting or chemical means.
- Provide a "profile" on the metal surface by roughening the surface. This should be done ideally by grit blasting (8-40 mesh grit), or by grinding with a coarse wheel or abrasive disc pad. An abrasive disc may be used provided white metal is revealed. Do not 'feather edge' epoxy materials. Epoxy material must be 'locked in' by defined edges and a good 3 - 5 mil profile.
- Metal that has been handling sea water or other salt solutions should be grit blasted and high pressure water blasted and left overnight to allow any salts in the metal to 'sweat' to the surface. Repeat blasting may be required to 'sweat out' all the soluble salts. A test for chloride contamination should be performed prior to any epoxy application. The maximum soluble salts left on the substrate should be no more than 40 p.p.m. (parts per million).
- Chemical cleaning with Devcon Fast Cleaner 2000 Spray / Cleaner Blend 300 should follow all abrasive preparation. This will help to remove all traces of sandblasting, grit, oil, grease, dust or other foreign substances.
- Under cold working conditions, heating the repair area to 38°C - 43° C immediately before applying any of Devcon's Metal-filled Epoxies is recommended. This procedure dries off any moisture, contamination or solvents and assists the epoxy in achieving maximum adhesion to the substrate.
- Always try to make the repair as soon as possible after cleaning the substrate, to avoid oxidation or flash rusting. If this is not practical, a general application of FL-10 Primer will keep metal surfaces from flash rusting.

Mixing: Mix ratio - weight 11:1, by Volume 3.75:1

Stainless Steel Putty is formulated to be a dense mix that can be applied easily to overhead and vertical surfaces without running or sagging. Add the hardener to resin and mix thoroughly on a mixing board using a spatula. Do not mix in the containers.

Application:

For best results, product should be kept and applied at room temperature.

Stainless Steel Putty can be applied when temperatures are between 13°C and 52°C. Spread the putty over prepared surface with a putty knife. Press firmly to ensure maximum surface contact and avoid trapping air. To bridge large gaps or holes use fibreglass, sheet metal or wire mesh.

Cure:

A 12.7mm thick section of Devcon Stainless Steel Putty will harden at 24°C in 4 hours. The material will be fully cured in 16 hours at which time the material can be machined, drilled or painted. The actual cure time of epoxy is determined by the size of the mass of epoxy and the room temperature at time of repair.



Brunel Close, Park Farm
Wellingborough
Northants
NN8 6QX
01933 675299
01933 670800
ISS 2.0 18/02/02

SHELF LIFE

A shelf life of three years from date of manufacture can be expected when stored at room temperature (22°C) in their original containers.

PRECAUTION

For complete safety and handling information, please refer to the appropriate Material Safety Data Sheets prior to using this product.

ORDERING INFORMATION:

<u>Stock No</u>	<u>Unit size</u>
10271	Stainless Steel Putty (ST) 500g
15980	Primer FL-10 112g
19550	Fast Cleaner 2000 Spray 500ml
19510	Cleaner Blend 300 250ml

Warranty: Devcon will replace any material found to be defective. Because the storage, handling and application of this material is beyond our control we can accept no liability for the results obtained.

Disclaimer: All information on this data sheet is based on laboratory testing and is not intended for design purposes. ITW Devcon makes no representations or warranties of any kind concerning this data.

For technical assistance please call 01933 675299