

Permabond 737 is a toughened cyanoacrylate with improved impact and peel strength for maximum flexibility. Its increased temperature resistance and dark colour make Black Magic suitable for a wide range of applications. It bonds rapidly to a variety of surfaces including aluminium, steel (both zinc-plated and uncoated), plastics and rubbers.

Physical Properties

| Chemical Type | Ethyl cyanoacrylate | |
|---------------|---------------------|--|
| Colour | Black | |
| Viscosity | 3000 mPa.s | |
| Density | 1.1 | |

Typical Performance

| Gap Fill | | 0.5mm |
|----------------------------|-------------|----------------|
| | Rubber | 10 seconds |
| Handling Time [†] | Plastic | 10 seconds |
| | Metal | 30 seconds |
| Full Strength | | 24 hours |
| Tensile Strength | ASTM D-2095 | 25 MPa (steel) |
| Service Temperature* | | -40 to +120°C |

[†]Handling times can be affected by temperature, humidity and specific surfaces being bonded. Larger gaps or acidic surfaces will also reduce cure speed but this can be overcome by the use of Permabond C Surface Activator (CSA). *Higher temperatures may be endured for short periods, providing the parts are not unduly stressed.

Surface Preparation

Surfaces should be clean, dry and grease-free before applying the adhesive. Permabond Cleaner A is recommended for the degreasing of most surfaces. Some metals such as aluminium, copper and its alloys will benefit from light abrasion with emery cloth (or similar), to remove the oxide layer.

Adhesive Application

- ■Apply the adhesive sparingly to one surface (usually 1 drop is sufficient). Bring the components together quickly and correctly aligned.
- Apply sufficient pressure to ensure the adhesive spreads into a thin film.
- ■Do not disturb or re-align until curing is achieved, normally in a few seconds.
- ■Any surplus adhesive can be removed with Permabond Cleaner A.

NB:

- For difficult or porous surfaces, Permabond CSA activator is recommended.
- ■If bonding polypropylene, polyethylene, PTFE or silicone, prime first with Permabond Polyolefin Primer.

Sto

Storage and Handling

| Storage Temperature | 5 to 7°C |
|---|----------|
| Shelf Life Stored in original unopened containers | 6 months |

Users are reminded that all materials, whether innocuous or not, should be handled in accordance with the principles of good industrial hygiene. Full information can be obtained from the Material Safety Data Sheet.

Contact Permabond:

Europe: Tel. +44 (0)1962 711661 US: Tel. 00 1 732-868-1372

UK Helpline: 0800 975 9800 Helpline: 800-640-7599
Deutschland: 0800 10 13 177 info.americas@permabond.com
France: 0805 11 13 88 Asia: Tel. 00 886 939 49 3310

info.europe@permabond.com info.asia@permabond.com

www.permabond.com

The information given and the recommendations made herein are based on our experience and are believed to be accurate. No guarantee as to, or responsibility for, their accuracy can be given or accepted, however, and no statement herein is to be treated as a representation or warranty. In every case we urge and recommend that purchasers, before using any product, make their own tests to determine, to their own satisfaction, its suitability for their particular purposes under their own operating conditions.