

### Product Description

VIBRA-TITE 131 is a high strength, anaerobic thread locking compound. VIBRA-TITE 131 is design for permanent locking of threaded fasteners. The product performs on aluminum, steel, plated, stainless steel, and special alloy parts. VIBRA-TITE 131 exhibits good temperature and solvent resistant.

### Typical Applications

VIBRA-TITE 131 will lock and seal large fasteners (1" and larger). VIBRA-TITE 131 is used in applications where shock and vibration may cause the fastener to loosen.


### Properties of Uncured Material

Chemical Type	Anaerobic
Appearance	Red
Toxicity	Low
Solids	100%
Viscosity @ 25°C, cP	
Brookfield RVT,	
Spindle 3 @ 20 rpm	1200-2400
Specific Gravity	1.10

### Typical Curing Performance

#### Cure Speed

The cure speed is depended on temperature and substrate. The graph below shows the Breakaway Strength on M-10 Steel, Phosphate/oil, and Zinc finishes.



### Performance of Cured Material

	<b>Typical Values</b>
Fixture Time	15-20 min @ 72°F
Full Cure Time	24 hrs @ 72°F
Temperature Range	-60°F to 300°F (-51°C to 150°C)

#### Breakaway Strength

3/8" Plain Steel nut and bolt @24 hr 140-300 lb<sub>r</sub>-in

#### Environmental and Fluid Resistance (Shear strength values)

	<b>Typical Values</b>
Heat age	100%
Engine oil @ 150°C	80%
Brake fluid @ 150°C	90%
ATF @ 150°C	90%
50/50 water/ ethylene glycol @ 120°C	85%
Water @ 100°C	85%
Gasoline @ 25°C	100%
Diesel fuel @ 25°C	100%
Ethyl Alcohol @25°C	95%

### Instructions for Use

Ensure parts are clean, dry and free from oil and grease.

### Compatible Primers

Primers such as Vibra-TITE Excel 611 (Primer N) or Excel 612 (Primer T) can be used to speed the fixture time of the adhesive. Fixture times can improve by as much as 50%. The use of primers can result in lower strength and performance should be tested after full cure.

### Presentation

Bottles.....2ml, 10ml, 50ml, 250ml and liter



Anaerobic  
Permanent Strength Threadlocker  
131  
Product Data Sheet

## General Information

### Storage

Product should be stored in a cool and dry location at temperatures between -10 °C to 30 °C. Optimal storage is 22±4°C. Shelf life is 18 months from date of manufacture when stored at 22±4°C.

### Note

Vibra-TITE 131 lubricates during assembly and results in medium to high locking strength. Not recommended for use with most plastics as stress cracking can occur. Excellent environmental and chemical resistance. Product conforms to MIL-S-46163A , ASTM D-5363, NSF.

### Health & Safety in use

IRRITANT: Contains Methacrylate Esters which may irritate eyes, respiratory organs and skin. In case of contact with the skin, wash immediately with plenty of water.