

SYLGARD® 182 Silicone Elastomer

FEATURES

- Two-part, 10:1 mixing ratio
- Medium viscosity
- Long pot life
- Rapid heat cure
- Addition cure system:
no cure by-products
- Stable and flexible from -50°C to +200°C
- Clear
- Flexible rubber - protects against mechanical shock and thermal cycling stress at components
- Excellent dielectric properties

Optically clear elastomer

APPLICATIONS

- Designed to protect against moisture, environmental attack, mechanical and thermal shock as well as vibration especially when optically clear product is required.
- Typical applications include: encapsulation of amplifiers, coils, connectors, circuit boards, equipment modules, ferrite cores, solar cells and transformers.

TYPICAL PROPERTIES

Specifications writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales representative prior to writing specifications on this product.

CTM*	ASTM*	Property	Unit	Value
As supplied				
0050	D1084	Viscosity at 23°C (Base) ¹	mPa.s	5500
		Mixing ratio by weight (Base:Curing Agent)		10:1
0050	D1084	Viscosity at 23°C, immediately after mixing with Curing Agent ¹	mPa.s	4000
0055	D1824	Pot life at 23°C ²	hours	8
Physical properties, cured 4 hours at 65°C				
0176		Colour		Clear
0099	D2240	Durometer hardness, Shore A		53
0137A	D412	Tensile strength	MPa	7.5
0137A	D412	Elongation at break	%	130
0159A	D624	Tear strength - die B	kN/m	2.7
0022	D0792	Specific gravity at 23°C		1.05
		Volume coefficient of thermal expansion	1/K	9.6x10 ⁻⁴
		Coefficient of thermal conductivity	W/(m.K)	0.17
Electrical properties, cured 4 hours at 65°C				
0114	D149	Dielectric strength	kV/mm	22
0112	D150	Permittivity at 100Hz		2.40
0112	D150	Permittivity at 100kHz		2.49
0112	D150	Dissipation factor at 100Hz		0.001
0112	D150	Dissipation factor at 1kHz		0.001
0249	D257	Volume resistivity	Ohm.cm	2.0x10 ¹⁵

1. Brookfield LVF, spindle #4 at 60rpm

2. Time required for catalysed viscosity to double at 23°C.

* CTM: Corporate Test Method, copies of CTMs are available on request.

ASTM: American Society for Testing and Materials.

HOW TO USE

Substrate preparation

All surfaces should be cleaned and degreased with a suitable solvent prior to potting. Care should be taken to ensure that all solvent is removed.

For best adhesion, coat surfaces with DOW CORNING® 92-023 Primer or DOW CORNING® 1200 OS Primer, following the instructions and precautions given for use of these products.

Mixing

SYLGARD 182 Silicone Elastomer is supplied in lot matched kits consisting of base and curing agent in separate containers.

The two components should be thoroughly mixed using a weight or volume ratio of 10:1.

The pot life is 8 hours for catalysed SYLGARD 182 Silicone Elastomer at room temperature. The pot life can be extended to 30 days by refrigeration at -20°C.

Vacuum de-airing is recommended. A residual pressure of 10-20mm mercury applied for 30 minutes will sufficiently de-air the material.

Lowering the viscosity

The viscosity of SYLGARD 182 Silicone Elastomer may be reduced by addition of up to 10% of DOW CORNING® 200 Fluid 20 cS. Added quantities of less than 5% have little or no effect on either the physical or electrical properties while larger quantities of DOW CORNING 200 Fluid 20 cS will diminish the physical strength and hardness. The addition of DOW CORNING 200 Fluid 20 cS does not alter the amount of curing agent required.

How to apply

Apply the encapsulant, being careful to avoid air entrapment. Vacuum encapsulation is recommended for complex geometries.

For information on appropriate dispensing equipment for your application, please contact

Dow Corning.

Curing

SYLGARD 182 Silicone Elastomer should be cured using one of the following recommended schedules:

4 hours at 65°C, or
1 hour at 100°C, or
15 minutes at 150°C

Large components and assemblies may require longer times in order to reach the curing temperature.

Compatibility

In some cases, SYLGARD 182 Silicone Elastomer may fail to cure to optimum properties when in contact with certain plastics or rubbers. Cleaning the substrate with solvent or baking slightly above the cure temperature will normally eliminate the problem.

Certain chemicals, curing agents and plasticisers can inhibit cure. These include:

- Organo-tin compounds
- Silicone rubber containing organo-tin catalysts
- Sulphur, polysulphides, polysulphones and other sulphur containing materials
- Amines, urethanes, amides and azides.

HANDLING PRECAUTIONS

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE FROM YOUR LOCAL DOW CORNING SALES REPRESENTATIVE.

USABLE LIFE AND STORAGE

When stored at or below 32°C in the original unopened containers, this product has a usable life of 24 months from the date of production.

PACKAGING

SYLGARD 182 Silicone Elastomer is available in standard industrial container sizes. For details please refer to your Dow Corning sales office.

LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

HEALTH AND ENVIRONMENTAL INFORMATION

To support customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Health, Environment and Regulatory Affairs specialists available in each area.

For further information, please consult your local Dow Corning representative.

LIMITED WARRANTY - PLEASE READ CAREFULLY

The information contained herein is offered in good faith based on Dow Corning's research and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information shall not be used in substitution for customers' tests to ensure that Dow Corning's products are fully satisfactory for your specific applications. Dow Corning's sole warranty is that the product will meet its current sales specifications. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. UNLESS DOW CORNING PROVIDES YOU WITH A SPECIFIC, DULY SIGNED ENDORSEMENT OF FITNESS FOR USE, DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

SUGGESTIONS OF USE SHALL
NOT BE TAKEN AS
INDUCEMENTS TO INFRINGE
ANY PATENT.

Your Global Connection

At home or abroad - wherever your business takes you - you'll find the product supply, customer service and technical support you need to succeed available locally from Dow Corning. Whether you face a challenge that could benefit from Dow Corning's international experience, or you need a reliable, local source of supply for innovative solutions, just pick up the phone and call us.

To consult Dow Corning web site, type: www.dowcorning.com

DOW CORNING ASIA

Australia & New Zealand

Dow Corning Australia Pty Ltd.

Tel.: +61 1300 360 732

Fax: +61 2984 741 00

China

Dow Corning China Ltd.

Tel.: +86 21 6249 2316

Fax: +86 21 6249 2317

China

Dow Corning Asia (H.K.)

Tel.: +852 2835 0350

Fax: +852 2836 6650

India, Indonesia, Singapore, Malaysia & Philippines

Dow Corning Singapore Pte Ltd.

Tel.: +65 253 6611

Fax: +65 253 6070

Japan

Dow Corning Asia Ltd.

Tel.: +81 3 3287 1151

Fax: +81 3 3287 1059 & 1081

Japan

Dow Corning Toray Silicone Co Ltd.

Tel.: +81 3 3287 1010

Fax: +81 3 3287 1201

Korea

Dow Corning Korea Ltd.

Tel.: +82 2 551 7600

Fax: +82 2 551 6800

Taiwan

Dow Corning Taiwan Inc.

Tel.: +886 2 2713 6936

Fax: +886 2 2717 2209

Thailand

Dow Corning Thailand Ltd.

Tel.: +66 2 326 0773

Fax: +66 2 326 0767

DOW CORNING EUROPE

Germany, Austria, Switzerland & Eastern Europe

Dow Corning GmbH
GERMANY

Tel.: +49 (0)611 - 23 71

Fax: +49 (0)611 - 237 610

France & North Africa

Dow Corning France S.A.

Tel.: +33 (0)4 72 84 13 60

Fax: +33 (0)4 72 84 13 79

Italy & Eastern Mediterranean Countries

Dow Corning S.p.A.
ITALY

Tel.: +39 039 - 60 711

Fax: +39 039 - 68 996 60

Poland

Dow Corning Polska Sp. zo.o.

Tel.: +48 (0)22 645 14 46

Fax: +48 (0)22 645 14 40

United Kingdom, Eire, Nordic Countries, Benelux, South Africa & Middle East

Dow Corning
UNITED KINGDOM

Tel.: +44 (0)1 676 52 80 00

Fax: +44 (0)1 676 52 80 01

Spain & Portugal

Dow Corning Ibérica S.A.
SPAIN

Tel.: +34 93 36 36 900

Fax: +34 93 36 36 901

DOW CORNING NORTH AMERICA

Dow Corning Corporation

Tel.: +1 517 496 6000

Fax: +1 517 496 8026

DOW CORNING SOUTH AMERICA

Dow Corning do Brasil Ltda.

Tel.: +55 11 3759 4300

Fax: +55 11 3758 5727