

Electrical Insulation Materials



Light Electrical

®Araldite Casting Resin System

Araldite F
Araldite CY 208
Hardener HY 956 EN

Casting systems for processing and curing at room temperature or slightly higher temperatures

Encapsulating or potting of low voltage and electronic components

Applications

Casting

Processing

The flexibility of castings can be adapted to requirements by combining Araldit F and CY 208 resin in various proportions
Low tendency to cracking

Properties

Edition: July 2003
Replaces edition: June 2001

Product data

(Guideline values)

Modified, medium viscous, solvent free epoxy resin

Araldite F	Viscosity	at 25°C	mPa s	ca. 11 000
	Specific gravity	at 25°C	g/cm ³	1.17
	Flash point		DIN 51 758 °C	> 200
	Epoxy content		Eq/kg	5.25
As supplied form	Pale yellow liquid			
Hazardous decomposition products	Carbon monoxide, carbon dioxide and other toxic gases and vapours if burned			
Disposal	Regular procedures approved by national and/or local authorities			

Modified, low viscosity solvent free epoxy resin

Araldite CY 208	Viscosity	at 25°C	mPa s	ca. 3500
	Specific gravity	at 25°C	g/cm ³	1.13
	Flash point		DIN 51 758 °C	190-200
	Epoxy content		Eq/kg	2.35
As supplied form	Clear liquid			
Hazardous decomposition products	Carbon monoxide, carbon dioxide and other toxic gases and vapours if burned			
Disposal	Regular procedures approved by national and/or local authorities			

Formulated, low viscosity polyamine hardener

Hardener HY 956 EN	Viscosity (Hoeppler)	at 25°C	mPa s	ca. 450
	Specific gravity	at 25°C	g/cm ³	1.02
	Flash point		DIN 51 758 °C	180
As supplied form	Clear, pale yellow liquid			
Hazardous decomposition products	Carbon monoxide, carbon dioxide and other toxic gases and vapours if burned			
Disposal	Regular procedures approved by national and/or local authorities			

Product data

(Guideline values)

Fillers

The chemical reaction initiated by mixing resin and hardener results in the generation of exothermic heat. The peak temperatures attained are determined by the initial temperature, size and shape of the casting being produced.

Unfilled resin systems are suitable only for manufacturing castings weighing up to about 500 grams. Mineral fillers should be added to dissipate heat and damp the exothermic reaction when producing large castings.

There is very little exothermic reaction when producing very small castings or thin layers as the generated heat is rapidly dissipated. Curing is consequently delayed and the surfaces of castings may remain tacky. In such cases, an infrared heater or oven should be used to effect full curing.

The addition of powdered inorganic fillers such as silica flour, microdol, chalk flour, Alumina, aluminium hydroxide etc., has been found to offer considerable advantages in many applications.

Specifically, the use of such fillers:

- enhance important mechanical and electrical properties
- reduce shrinkage and exothermic temperature rise during gelling and cure
- impart a lower coefficient of thermal expansion
- improve thermal conductivity
- impart a greater elasticity modulus whilst reducing elongation at break

Araldite Colouring Pastes

Castings are best coloured by adding epoxy based Araldite colouring paste. Such pastes have hardly any effect on the processing or end properties of the casting resin system.

The colouring paste should normally be added to the resin component and mixed with it until homogeneous colouration results. Filled, highly viscous resin components are best heated to 40-60°C to facilitate uniform dispersion of the colouring paste.

Coloured resin or mixes of several colouring pastes and resins are stable for some considerable time if stored at room temperature (see instruction sheet, Publ. No. 24 849/e).

Storage

Store the components in a dry place at 18-25°C, in tightly sealed original containers. Under these conditions, the shelf life will correspond to the expiry date stated on the label. After this date, the product may be processed only after reanalysis. Partly emptied containers should be tightly closed immediately after use.

For information on waste disposal and hazardous products of decomposition in the event of a fire, refer to the Material Safety Data Sheets (MSDS) for these particular products.

Processing

The resin component should be stirred and homogenized in the original container before use.

The casting mix is best prepared by heating the resin up to 40-50°C before stirring in the hardener. Brief degassing of the mix under 5-10 mbar vacuum improves the mixture homogeneity and enhances the dielectric properties of the castings.

The very low viscosity Araldite CY 208 provides flexible castings, whereas the medium viscosity Araldite F provides more rigid castings.

The viscosity of the casting mix and/or the hardness of the castings can be varied by adjusting the mix ratio of the two resins.

Premixes of the two resins have a shelf life at room temperature of several months.

To reduce the curing time, the casting is often gelled at room temperature and then post-cured for 2-6 hours at 60-80°C. Small castings can be processed and directly cured at slightly higher temperatures (40-60°C).

Temperature exothermic rise on curing (e.g. at higher curing temperatures or/and large casting volumina) can be kept within acceptable limits by adding fillers to the mix.

System	1	2	3	4
Mix ratios	parts by weight			
Araldite F		100	80	50
Araldite CY 208	100		20	50
Hardener HY 956 EN	11	22	20	16.5

System	1	2	3	4
Processing data (Guideline values)	Initial viscosity (Hoeppler) mPa s at 25°C			
	1800	7000	2500	3500
	Pot life (min at 25°C)			
	-	-	-	30-40
	Minimum curing time			
	h at 25°C			72
	h at 100°C			4*
	h at 120°C			1 ^{1/2*}

*large castings should be precured at room temperature

Properties

Guideline values determined on standard test specimens cured for 24 h/RT+6 h/60°C

System		1	2	3	4
Flexural strength(ISO 178)					
max. bending stress	Mpa	-	125	120	90
E modulus	Mpa	-	5100	5000	4900
Impact strength(ISO 179)					
	kJ/m ²	-	17	16	22
Tensile strength(ISO/R 527)					
at 23°C					
tensile stress (max.)	Mpa				
tensile stress (break)	MPa				
elongation (max.)	%				
elongation (break)	%				
Martens dimensional stability under heat (DIN 53 458)	°C	-	83	70	35
Loss factor tan δ (DIN 53 483)					
50 Hz					
at 23°C	%	-	0.25	1.00	3.10
at 40°C	%	-	0.40	1.90	6.00
at 50°C	%	-	1.00	4.10	7.40
at 60°C	%	-	1.30	8.50	9.90
Dielectric constant ε _r (DIN 53 483)					
50 Hz					
at 23°C		-	4.20	4.30	4.80
at 40°C		-	4.50	4.60	4.70
at 50°C		-	4.80	4.90	4.95
at 60°C		-	5.10	5.25	5.35
Volume resistivity ρ (DIN 53483)					
at 23°C	Ω·cm	-	2,0.10 ¹⁶	8,7.10 ¹⁵	4,2.10 ¹⁴
at 40°C	Ω·cm	-	3,2.10 ¹⁵	4,1.10 ¹⁴	5,5.10 ¹²
at 60°C	Ω·cm	-	9,5.10 ¹³	8,1.10 ¹¹	7,6.10 ¹⁰
Dielectric strength (IEC 243)					
2 mm plate (50 Hz) at 25°C					
1 minute value	kV/mm	5	21	-	-

Notes

Industrial hygiene

Mandatory and recommended industrial hygiene procedures should be followed whenever our products are being handled and processed. For additional information please consult the corresponding Safety Data Sheets and the brochure "Hygienic precautions for handling plastics products of Huntsman (Publ. No. 24264/e).

Handling precautions

Safety precautions at workplace:	
protective clothing	yes
gloves	essential
arm protectors	recommended when skin contact likely
goggles/safety glasses	yes
respirator/dust mask	recommended
Skin protection	
before starting work	Apply barrier cream to exposed skin
after washing	Apply barrier or nourishing cream
Cleansing of contaminated skin	Dab off with absorbent paper, wash with warm water and alkali-free soap, then dry with disposable towels. Do not use solvents
Clean shop requirements	Cover workbenches, etc. with light coloured paper Use disposable beakers, etc.
Disposal of spillage	Soak up with sawdust or cotton waste and deposit in plastic-lined bin
Ventilation:	
of workshop	Renew air 3 to 5 times an hour
of workplace	Exhaust fans. Operatives should avoid inhaling vapours.

First Aid

Contamination of the **eyes** by resin, hardener or casting mix should be treated immediately by flushing with clean, running water for 10 to 15 minutes. A doctor should then be consulted.

Material smeared or splashed on the **skin** should be dabbed off, and the contaminated area then washed and treated with a cleansing cream (see above). A doctor should be consulted in the event of severe irritation or burns. Contaminated clothing should be changed immediately.

Anyone taken ill after **inhaling** vapours should be moved out of doors immediately. In all cases of doubt call for medical assistance.

Vantico Ltd
Advanced Materials
® Registered trademark



All recommendations for use of our products, whether given by us in writing, verbally, or to be implied from results of tests carried out by us are based on the current state of our knowledge. Notwithstanding any such recommendations the Buyer shall remain responsible for satisfying himself that the products as supplied by us are suitable for his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility therefore. The Buyer shall ensure that the intended use of the products will not infringe any third party's intellectual property rights. We warrant that our products are free from defects in accordance with and subject to our general conditions of supply.