

# MOLYKOTE® PTFE-N UV Anti-Friction Coating

Air-curing dry lubricant

## Features

- Very low coefficient of friction
- Colorless, therefore nonstaining
- Detectable on the surface

## Composition

- PTFE
- Binder
- Solvent
- Ultraviolet indicator

## Applications

Suitable for rubber guides, sliding doors, furniture hinges, small mechanisms in office machines and sunroof seals. For nearly all material combinations, such as metal/metal, plastic/metal, plastic/plastic combinations, involving slow to medium movements and medium loads. The UV indicator enables the end user to readily inspect and confirm, using UV inspection lamps, that the product has been applied to the substrate.

## How to use

### Surface preparation

First, clean and degrease the surface that will be coated with MOLYKOTE® PTFE-N UV Anti-Friction Coating. Phosphatization or sandblasting (180 grid) increases the adhesion and service life.

### How to apply

Stir the anti-friction coating thoroughly before applying by spraying, dipping, centrifuging or brushing. Recommended dry-film thickness: 5 to 20 µm.

### Curing

120 minutes at 20°C.

### Solubility

Thinning can be carried out using MOLYKOTE® L13 Thinner.

## Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE® sales representative prior to writing specifications on this product.

Standard <sup>(1)</sup>	Test	Unit	Result
	Color		Colorless
<b>Physical properties</b>			
DIN 53211/4	Viscosity at 20°C (DIN4 cup)	s	12
DIN 53217/2	Density at 20°C	g/ml	0.87
	Solid content <sup>(2)</sup>	%	23
	Storage life	months	24
<b>Temperature</b>			
	Service temperature range	°C	-180 to +240
	Drying time at 20°C	min	5-10
	Curing time	min/°C	120/20
<b>Load-carrying capacity, wear protection, service life<sup>(3)</sup></b>			
ASTM D2714	LFW-1, rotating F=680 N, n=72 min <sup>-1</sup> , v=7.9 m/minute no. of revolutions x1000 to µ=0.1		b=6 p=30 s=10

<sup>(1)</sup>DIN: Deutsche Industrie Norm. ASTM: American Society for Testing and Materials.

<sup>(2)</sup>Calculated value.

<sup>(3)</sup>Surface pretreatment: b = blank, p = phosphated, s = sandblasted.

## Handling precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

## Usable life and storage

When stored at or below 20°C in the original unopened containers, this product has a usable life of 24 months from the date of production.

Because it is an aerosol, punctures should be avoided, and containers should be kept away from heat, sparks and open flame.

## **Packaging**

This product is available in different standard container sizes as shown on **molykote.com**. Detailed container size information should be obtained from your nearest MOLYKOTE® sales office or MOLYKOTE® distributor.

*DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.  
© 1997-2022 DuPont.*

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.