

Advanced Materials**RenCast[®] CW 2215 / Ren[®] HY 5160 or HY 5161
or HY 5162****CASTING RESIN
MINERAL FILLED EPOXY SYSTEM IN A RANGE OF REACTIVITIES****KEY
PROPERTIES**

- Suitable for full or face castings
- Cures at room temperature
- Cure rate determined by choice of hardener
- Layers up to 80mm thick can be cast in a single operation
- Readily machinable when cured
- Mixes can be pigmented with colouring pastes DW 0131-DW 0137

APPLICATIONS

- Construction of foundry patterns
- Jigs and fixtures
- Copy-milling models
- Working models for the ceramics industry
- Suitable for a wide range of applications

PRODUCT DATA

Property	Unit	RenCast [®] CW 2215	Ren [®] HY 5160	Ren [®] HY 5161	Ren [®] HY 5162
Appearance Colour	visual	Paste Pale beige	Clear liquid Pale yellow	Clear liquid Pale yellow	Clear liquid Pale yellow
Viscosity at 25°C (ISO 2555)	mPas	110'000 - 190'000**	30 - 50**	35 - 55**	30 - 70**
Density	g/cm ³	1.7	1.0	1.0	1.0

** Specified data are on a regular basis analysed. Data which is described in this document as 'typical' is not analysed on a regular basis and is given for information purposes only. Data values are not guaranteed or warranted unless if specifically mentioned.

TYPICAL SYSTEM DATA**PROCESSING**

Mix ratio	Parts by weight		
RenCast [®] CW 2215	100	100	100
Ren [®] HY 5160	20	-	-
Ren [®] HY 5161	-	20	-
Ren [®] HY 5162	-	-	20

Mix the two components thoroughly in the ratio indicated.
If fine details are to be reproduced, a thin layer of mixed resin and hardener should be applied to the mould surface using a short bristle brush before casting.
Evacuated material will improve properties. Post-curing will improve final properties.

PROPERTIES

Resin/Hardener mix:	Volume	Unit	CW 2215 HY 5160	CW 2215 HY 5161	CW 2215 HY 5162
Appearance			Yellow	Yellow	Yellow
Viscosity at 25°C		m Pa s	4,000	5,000	5,000
Pot life at 25°C	1000 ml	min	120	45	25
Max. Layer thickness		mm	80	20	10
Demoulding time		h	16	12	10

After cure: 7 days at 25°C / 14 hours at 40°C

Density	ISO 1183	g/cm ³	1.6	1.6	1.6
Hardness	ISO 868	Shore D	85-90	85-90	85-90
Coefficient of thermal expansion	ISO 11359	10 ⁻⁶ k ⁻¹	45	45	45
Deflection temperature	ISO 75	°C	50-55	55-60	60-65
Compressive strength	ISO 604	MPa	80-90	80-90	80-90
Compressive modulus	ISO 604	MPa	3,500-4,000	3,500-4,000	3,500-4,000
Flexural strength	ISO 178	MPa	65-75	60-70	60-70
Linear shrinkage		mm/m	0.1	0.7	0.3
Abrasion resistance	Taber	mm ³ /100U	90-100	90-100	90-100

STORAGE

Provided that RenCast® CW 2215 and Ren® HY 5160 / HY 5161 / HY5162 are stored in a dry place in their original, properly closed containers at the storage temperatures mentioned in the MSDS they will have the shelf lives indicated on the labels. Partly emptied containers should be closed immediately after use.

WORKING CONDITIONS

The product should be used when in the temperature range 18-25°C.

PACKAGING

System	CW 2215	HY 5160	HY 5161	HY 5162
Quantity and Weight	1 x 10kg	4 x 2kg	4 x 2kg	4 x 2kg
Quantity and Weight	6 x 750gr	6 x 150gr	6 x 150gr	6 x 150gr

HANDLING PRECAUTIONS

Caution

Our products are generally quite harmless to handle provided that certain precautions normally taken when handling chemicals are observed. The uncured materials must not, for instance, be allowed to come into contact with foodstuffs or food utensils, and measures should be taken to prevent the uncured materials from coming in contact with the skin, since people with particularly sensitive skin may be affected. The wearing of impervious rubber or plastic gloves will normally be necessary; likewise the use of eye protection. The skin should be thoroughly cleansed at the end of each working period by washing with soap and warm water. The use of solvents is to be avoided. Disposable paper - not cloth towels - should be used to dry the skin. Adequate ventilation of the working area is recommended. These precautions are described in greater detail in the Material Safety Data sheets for the individual products and should be referred to for fuller information.

Huntsman Advanced Materials

(Switzerland) GmbH
Klybeckstrasse 200
4057 Basel
Switzerland

Tel: +41 (0)61 299 11 11
Fax: +41 (0)61 299 11 12

www.huntsman.com/advanced_materials
Email: advanced_materials@huntsman.com



Huntsman Advanced Materials warrants only that its products meet the specifications agreed with the user. Specified data are analysed on a regular basis. Data which is described in this document as 'typical' or 'guideline' is not analysed on a regular basis and is given for information purposes only. Data values are not guaranteed or warranted unless if specifically mentioned.

The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication. While all the information and recommendations in this publication are, to the best of Huntsman Advanced Material's knowledge, information and belief, accurate at the date of publication, nothing herein is to be construed as a warranty, whether express or implied, including but without limitation, as to merchantability or fitness for a particular purpose. In all cases, it is the responsibility of the user to determine the applicability of such information and recommendations and the suitability of any product for its own particular purpose.

The behaviour of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which are not known to Huntsman Advanced Materials. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Advanced Materials containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards.

Hazards, toxicity and behaviour of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behaviour should be determined by the user and made known to handlers, processors and end users.

Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC or of its affiliated companies including without limitation, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., Huntsman Advanced Materials (UAE) FZE, Huntsman Advanced Materials (Guangdong) Company Limited, and Huntsman Advanced Materials (Hong Kong) Ltd.

Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not limited to Huntsman Advanced Materials LLC in the USA and Huntsman Advanced Materials (Europe) BVBA in Europe.

All trademarks mentioned are either property of or licensed to Huntsman Corporation or an affiliate thereof in one or more, but not all, countries.

Copyright © 2012 Huntsman Corporation or an affiliate thereof. All rights reserved.